



EUROPEAN PATENT SPECIFICATION

45 Date of publication of patent specification: **02.11.94** **61** Int. Cl.⁵: **B29C 65/06, B29C 65/56**

21 Application number: **80309075.1**

22 Date of filing: **17.08.80**

64 Method and apparatus for joining thermoplastic parts.

30 Priority: **28.08.89 US 399091**

43 Date of publication of application:
06.03.91 Bulletin 91/10

43 Publication of the grant of the patent:
02.11.94 Bulletin 94/44

64 Designated Contracting States:
DE GB IT

66 References cited:

WO-A-79/00342	WO-A-88/08785
DE-A- 2 034 071	FR-A- 2 242 189
FR-A- 2 255 157	US-A- 2 942 748
US-A- 3 184 353	US-A- 3 444 018
US-A- 3 640 655	

73 Proprietor: **AT&T Corp.**
32 Avenue of the Americas
New York, NY 10013-2412 (US)

72 Inventor: **Arnett, Jaime Ray**
8525 Los Robles Road
Noblesville, Indiana 46060 (US)
Inventor: **O'Connor, Robert Joseph**
2783 West Lake Drive
Greenfield, Indiana 46140 (US)

74 Representative: **Johnston, Kenneth Graham et al**
AT&T (UK) LTD.
AT&T Intellectual Property Division
6 Mornington Road
Woodford Green Essex, IG8 OTU (GB)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

EP 0 415 615 B1

Description

Technical Field

This invention relates to a method and apparatus for permanently joining plastic parts together, and more particularly to a method wherein thermoplastic parts are welded.

Background of the Invention

The use of plastics has expanded significantly in recent years, in part because they are inexpensive, easily molded into desired shapes, electrically non-conductive, lightweight and offer long service life. The joining of plastics is crucial to the more widespread use of these materials and, although plastics have been joined for many years, there is a need for new welding techniques that are simpler, faster and less expensive. Plastics can be joined by mechanical fasteners, adhesives or welding. Mechanical fasteners are common and are suitable for most materials but can be expensive and may not provide a permanent (when desirable) joint or adequate properties. Adhesives give good properties and sound joints but can be difficult to handle, require care with joint and surface preparation, and are slow. Welding is ideally suited to use in the mass production industries as the techniques are economical, simple, fast, reliable and capable of making joints with static mechanical properties close to those of the parent material.

One conventional technique for joining plastic parts together is the use of hooks and latches which interlock when pressed together. However, those very features needed to effectively attach one plastic part to another now make the mold tool more complicated and expensive. Intricately shaped plastic parts are more expensive than simply shaped ones because their molds include tools that must be sequentially removed from the finished part in multiple directions.

Thermoplastic parts may be temporarily joined by press fitting where a shaft is pressed into a boss of substantially the same shape but slightly smaller dimensions. However, after a period of time these parts are prone to separate - especially when subjected to moisture, temperature variations, vibration or frequent handling. To overcome this problem, manufacturers use solvents to soften thermoplastic parts which are then clamped or pressed together until the solvent evaporates. Similarly, the use of adhesives or bonding materials generally require long curing periods and contribute to air pollution. Long curing periods are inconsistent with modern manufacturing techniques such as just-in-time fabrication used to reduce factory inventory and lower costs. Although the evaporation rate of a

solvent or the curing rate of a bonding material may be hastened by heating, it is desirable to simplify, further shorten, and thereby cost reduce the process.

A survey of techniques for permanently joining plastics is disclosed in a paper entitled "Welding Plastics for the Automotive Industry" by Martin N. Watson, SAE Technical Paper Series 860581, February 24-28, 1985. The disclosed techniques include: (i) *Ultrasonic Welding* - a bonding process that utilizes high frequency mechanical vibrations. The parts to be assembled are held together under pressure and then subjected to ultrasonic vibration at right angles to the contact area so that longitudinal vibrations are transmitted through the component. Although ultrasonic welding is well suited to mass production and offers high speed, tooling is expensive. (ii) *Spin Welding* - friction heating due to spin, angular or orbital rotation of thermoplastic material to cause melting/welding to occur. A disadvantage of the spin welding process is that in its simplest form, it is only suitable for applications in which at least one of the components is circular and requires no angular alignment (iii) *Vibration Welding* - frictional heating generated by the relative movement between two parts to be welded which are held under pressure. Once molten material has been generated at the joint interface, vibration is stopped, the parts are aligned and the weld solidifies on cooling. Weld times of 1-5 seconds are possible with applied vibrations being typically 100-240 Hz, 150mm amplitude, and the pressure of 1-4N/mm². This technique is frequently used for the welding of various mass produced thermoplastic components. While these various techniques are generally useful, it is desirable to further decrease weld time, and to simplify the equipment needed to carry out the welding process.

Summary of the Invention

First and second thermoplastic parts are joined by a novel process that uses frictionally created heat to perform welding. The first thermoplastic part includes a shaft, and the second thermoplastic part includes a cavity that has substantially the same shape as the shaft but is slightly smaller in cross-section. The shaft is thrust into the cavity at a velocity sufficient to cause melting along the mating surfaces to occur and, after a brief cooling period, the parts are permanently welded.

In one illustrative embodiment of the invention, shafts and cavities are molded into the body of thermoplastic parts to be joined.

In another illustrative embodiment of the invention, the shaft is an independent part, made from thermoplastic material, and used to join two other

parts together, one of which includes a cavity also made from thermoplastic material.

It is an advantage of the present invention that the shafts and cavities can be molded using tools that separate with a straight pull.

Brief Description of the Drawing

FIG. 1 is a housing for telephone equipment made from thermoplastic materials in accordance with the invention;

FIG. 2 discloses one part of the FIG. 1 housing showing an extended cavity and a shaft in accordance with the invention;

FIG. 3 is a cross-section of the FIG. 1 housing that illustrates how the shafts and cavities are joined;

FIG. 4 discloses the cavity within a boss in detail showing illustrative dimensions;

FIG. 5 discloses the shaft in great detail showing illustrative dimensions thereof;

FIG. 6 discloses a shaft made from thermoplastic material in accordance with the invention;

FIG. 7 discloses the use of the FIG. 6 shaft in joining two other parts together.

FIG. 8 discloses a fixture for holding the thermoplastic parts of FIG. 1 for welding in accordance with the invention; and

FIG. 9 discloses the fixture of FIG. 8 combined with an air cylinder that cooperate to perform welding in accordance with the present invention.

Detailed Description

The welding of plastics is confined to thermoplastic materials (i.e., those which can be melted or softened by heat without degradation). Examples of thermoplastic materials include: Acrylonitrile-Butadiene-Styrene (ABS), polycarbonate, and polyvinyl chloride (PVC). Thermoset plastics, on the other hand, do not soften on heating and cannot be welded. Examples of thermoset materials include: Formica™, phenolics and Bakelite™. The present invention is concerned with a novel technique for joining parts made from thermoplastic materials.

FIG. 1 discloses a thermoplastic housing 100 for containing electrical components such as used in providing telephone service. Housing 100 contains, for example, components for filtering radio frequency electrical signals from a telephone line. It is adapted to be series-connected with the telephone line using modular plugs (not shown) at each end thereof. During normal use, a modular plug fits into opening 15 to electrically engage the circuitry contained within the housing. Housing 100 comprises a pair of mating parts 10, 20 which meet along seam 120. In this example embodiment,

parts 10 and 20 are identical.

FIG. 2 reveals the inside structure of part 10 which is molded from a thermoplastic material such as ABS. Protrusions 23 of part 10 are positioned to interlock with complementary recessed areas of mating part 20. Similarly, recessed areas 24 of part 10 are positioned to interlock with complementary protrusions of mating part 20. These recessed areas and protrusions operate to guide parts 10 and 20 together during manufacture and provide structural stability thereafter. Molded into the structure of part 10 are boss 11 and shaft 12. Within boss 11 is a cavity 13 which is adapted to receive a shaft, of slightly larger dimensions, for the purpose of joining parts 10 and 20 together.

FIG. 3 is a cross-section view of housing 100 that illustrates the manner in which shafts 12, 21 are joined to bosses 22, 11 respectively. Dimensional details of boss 11 are shown in FIG. 4 while dimensional details of shaft 21 are shown in FIG. 5.

Referring now to FIG. 4, there is shown a cross-section view of part 10 in the region of boss 11. Of particular importance is the shape of cavity 13 within boss 11 relative to the shape of mating shaft 21. In this illustrative embodiment, entrance 14 to cavity 13 is beveled to facilitate entry of mating shaft 21 during manufacture. The cavity 13 tapers from an entrance diameter of .097 inches (0.25cm) to a bottom diameter of .092 inches (0.23cm). Since the length of cavity 13 is .6 inches, a draft angle α of approximately .5 degrees is formed. Comparing these dimensions now with the shaft shown in FIG. 5, it will be noticed that the shaft 21 is approximately .003 inches larger at both the top and bottom thereof. Note also that the length of the shaft 21 is slightly smaller than the length of cavity 13 - a feature that allows for boss and shaft length tolerance and engagement variations. These dimensions define draft angle β which is substantially the same as draft angle α .

Shaft 21 will not completely enter cavity 13 without the application of force. Even after the application of force, shaft 21 and boss 11 may not stay permanently joined when subjected to moisture, temperature variations, vibration or repeated handling. Furthermore, if shaft 21 and boss 11 are not made of the same material, there may be a different thermal coefficient of expansion causing them to loosen as the temperature changes. It has been discovered, however, that shaft 21 can be thrust into cavity 13 at velocities sufficient to cause surface melting of the thermoplastic materials. After a brief cooling period (less than 1 second), shaft 21 is welded to boss 11. It has also been discovered, that a number of factors cooperate in the welding process. These factors include, but are not limited to: (1) relative dimensions of the shaft and cavity, (2) insertion speed, (3) thermoplastic materials

used, (4) surface finish, (5) length of the shaft and cavity, (6) cross-section geometry of shaft/cavity (i.e., round, square, oval), and (7) draft angle.

In the example embodiment when shaft and cavity are joined slowly, no welding occurs, and removal of the shaft from the cavity requires approximately 40 pounds of force. When the shaft and cavity are thrust together at a higher velocity, welding occurs and approximately 100 pounds (440N) of force are required to remove the shaft from the cavity. After removal, typical evidence of welding is illustrated in region 62 of the shaft shown in FIG. 6. In a preferred embodiment of the invention, shaft 21 and boss 11 each have round cross-sections and are made from ABS material. Using the indicated shaft and cavity dimensions (see FIG. 4 and 5), welding commences at speeds exceeding 50 inches per second (127cm/sec). In the preferred embodiment of the invention, velocities (203cm/sec) 80 inches per second are used.

Referring once again to FIG. 6, shaft 600 is a separate and distinct parts that is used like a nail. Shaft 600 includes shaft portion 61 that is generally smooth and straight, and becomes gradually narrower as it recedes from head portion 60. Shaft 600 is made from a thermoplastic material. A typical application of shaft 600 is shown in FIG. 7 where it is operative in permanently joining apparatus 80 to part 70. In this application, apparatus 80 need not be made from thermoplastic materials since it is captured by the cooperation of head portion 60 of shaft 600 and the upper portion of boss 71. In this particular application, the length of shaft 61 does not extend to the bottom of the cavity, and a region 72 is formed where air is compressed by the movement of the shaft into the cavity. This compressed air may be released to the outside through port 73. In the event that the designer does not wish to blemish the surface of part 70 with a hole, but is concerned that the air pressure in region 72 may be excessive, pressure can be decreased by using a shorter shaft 61 in order to increase the volume of region 72. Alternatively, longitudinal grooves along shaft 61 or a hole through its center can be used to eliminate pressure in region 72, particularly when shaft 61 completely fills the cavity 13.

FIG. 8 discloses equipment used in holding the thermoplastic housing 100 shown in FIG. 1. The equipment comprises an upper fixture 810 that joins with a lower fixture 820 during the welding process. The fixtures are made from machined aluminum stock, although other materials are acceptable and are typically chosen based on considerations such as cost and required durability. Upper fixture 810 includes alignment pins 802, 803 that mate with receiving holes 822, 823 of the lower fixture 820. Also contained in lower fixture 820 is a

cavity 825 for receiving the thermoplastic housing to be welded. The depth of the cavity 825 corresponds to the finished depth of the thermoplastic housing so that when upper and lower fixtures 810, 820 are thrust together, the fixture absorbs the energy needed to halt further compression of the thermoplastic housing rather than the housing itself. Cavity 825 is shaped to receive the housing as well as a tool for removing it after welding is complete.

FIG. 9 provides additional detail surrounding the actual welding process. Apparatus 900 is a compact air cylinder that comprises a rigid housing 910 having a solid top surface and a solid bottom surface which includes a hole through which a shaft 940 protrudes. Attached to the top of shaft 940 is a generally flat plate that forms a seal with the inside walls of housing 910 and is driven up and down, much like a piston in an automobile engine, by air pressure delivered and removed via air supply lines 920 and 930. Supply line 920 delivers or removes air from the top surface of the plate while supply line 930 removes or delivers air to the bottom surface of the plate. Apparatus 900 is a commercially available compact air cylinder such as Stock No. 2A713 manufactured by Speedaire. Shaft 940 includes external threads 941 for joining with corresponding internal threads 801 of the upper fixture 810. Shaft 940 further includes slot 942 for holding the shaft 940 while being joined with upper fixture 810. Once the shaft 940 is joined to the upper fixture 810, which is inserted in lower fixture 820, the thermoplastic housing 100 awaits the downward thrust that causes welding. This downward thrust occurs when the air pressure in supply line 920 is increased to 90 psi in this example embodiment Air rushes out of supply line 930 as the shaft 940 is driven downward. The downward movement of shaft 940 reaches a velocity of approximately 80 inches/second which is sufficient to cause acceptable welding of thermoplastic housing 100 using ABS materials having the dimensions shown in FIGS. 4-5. Thereafter, the upper and lower fixtures are separated when compressed air is delivered to the air cylinder 900 via supply line 930 and evacuated via supply line 920. This causes the shaft to be driven upward thus exposing the welded product for removal from the bottom fixture 820. Cooling is virtually instantaneous and assembly of the thermoplastic housing 100 is now complete.

It is understood that the disclosed welding technique may be advantageously used in connection with a wide variety of thermoplastic materials and a multitude of products. The deck and shell of a telephone handset may be permanently joined using the present invention as well as plastic toys, automobile parts, appliances and various electronic products to name but a few. Further, the invention

finds application as a thermoplastic nail in which a hammer is used for join it with a mating thermoplastic cavity. So long as the velocity exceeds some minimum value determined by the thermoplastic materials used, as well as the relative dimensions of the nail and the cavity, welding will occur and the advantages of the invention will be realized.

Claims

1. A method for welding first (10) and second (20) thermoplastic parts together, characterised in that the first part includes a shaft (12), and the second part includes a cavity (22) substantially of the same general shape as the shaft but of slightly smaller average cross-section and in that the method comprises the steps of: inserting the shaft of the first part into the cavity of the second part; and thrusting the shaft further into the cavity at sufficient velocity to cause melting of the thermoplastic material of the parts in at least one region where the shaft and cavity are in contact melting of the thermoplastic material being caused by frictional contact in an axial direction, during axial thrust of the shaft into the cavity, whereby welding occurs after the melted thermoplastic material cools.
2. The method of claim 1 wherein the thermoplastic material of the first (10) and second (20) parts is identical.
3. The method of claim 2 wherein the thermoplastic material comprises Acrylonitrile-Butadiene-Styrene.
4. The method of claim 3 wherein the velocity of insertion of the shaft (12) into the cavity (22) exceeds fifty inches per second (127cm/sec).
5. The method of claim 1 wherein the cross-section of the shaft (12) maintains its general shape, but gradually becomes wider along its length from its initial point of entry into the cavity (22).
6. The method of claim 5 wherein the cross-section of the shaft (12) is substantially circular.
7. Apparatus for permanently joining first (810) and second (820) parts, the first part including a shaft (802) made from thermoplastic material, and the second part including a cavity (822) having substantially the same shape as the shaft but being of slightly smaller average

cross-section and having walls made from thermoplastic material, CHARACTERIZED BY: a fixture (820) for supporting at least one of the first and second parts prior to the permanent joining of same; and means (900) for thrusting said first and second parts together in a manner such that the shaft moves through the cavity at a velocity sufficient to cause welding of their contacting surfaces.

8. The apparatus of claim 7 wherein the shaft (802) and the walls of the cavity (822) comprise identical thermoplastic material.
9. The apparatus of claim 8 wherein the thermoplastic material comprises Acrylonitrile-Butadiene-Styrene.
10. The apparatus of claim 9 wherein the velocity that the shaft moves through the cavity exceeds 50 inches per second (127cm/sec).

Patentansprüche

1. Verfahren zum Schweißen von ersten (10) und zweiten (20) Kunststoffteilen miteinander, dadurch gekennzeichnet, daß das erste Teil einen schaft- oder stiftförmigen Fortsatz (12) und das zweite Teil einen Hohlraum (22) umfaßt, der im wesentlichen die gleiche Form wie der Fortsatz aufweist, jedoch etwas geringeren Querschnitt besitzt und daß das Verfahren folgende Schritte aufweist: der schaft- oder stiftförmige Fortsatz des ersten Teils wird in den Hohlraum des zweiten Teils eingefügt; der Fortsatz wird weiter in den Hohlraum mit genügender Geschwindigkeit gestoßen, um das thermoplastische Material der Teile an mindestens einer Stelle zum Schmelzen zu bringen, an der der Fortsatz und der Hohlraum in Kontakt zueinander stehen, und zwar wird das Schmelzen des thermoplastischen Materials durch Reibkontakt in axialer Richtung während des axialen Stoßes des Fortsatzes in den Hohlraum erzeugt, wobei das Verschweißen stattfindet, nachdem das aufgeschmolzene thermoplastische Material abkühlt.
2. Verfahren nach Anspruch 1, dadurch gekennzeichnet, daß das thermoplastische Material des ersten (10) und zweiten (20) Kunststoffteils identisch ist.
3. Verfahren nach Anspruch 2, dadurch gekennzeichnet, daß das thermoplastische Material Acrylnitril-

Butadien-Styrol umfaßt.

4. Verfahren nach Anspruch 3, dadurch gekennzeichnet, daß die Einfügbewegung des schaft- oder stiel- förmigen Fortsatzes (12) in den Hohlraum (22) 50 Zoll/Sekunde (127 cm/s) übersteigt.
5. Verfahren nach Anspruch 1, dadurch gekennzeichnet, daß der Querschnitt des Fortsatzes (12) seine generelle Form beibehält, jedoch von der ur- sprünglichen Eintrittsstelle in den Hohlraum (22) entlang seiner Länge allmählich dicker wird.
6. Verfahren nach Anspruch 5, dadurch gekennzeichnet, daß der Querschnitt des Fortsatzes (12) im wesentlichen kreisförmig ist.
7. Vorrichtung zum dauernden Verbinden von er- sten (810) und zweiten (820) Teilen miteinander, wobei das erste Teil einen schaft- oder stiel- förmigen Fortsatz (802) aus thermoplasti- schem Material und das zweite Teil einen Hohlraum (822) mit im wesentlichen der glei- chen Form wie der Fortsatz, jedoch mit gering- fällig kleinerem Querschnitt sowie mit Wan- dungen aus thermoplastischem Material auf- weist, dadurch gekennzeichnet, daß eine Montagevorrichtung (820) zum Halten mindestens des ersten oder zweiten Teils vor deren dauerhafter Verbindung miteinander vor- gesehen ist, und daß eine Einrichtung (900) zum Zusammen- schieben der ersten und zweiten Teile mitein- ander in solcher Weise vorgesehen ist, daß sich der Fortsatz durch den Hohlraum mit ei- ner genügenden Geschwindigkeit bewegt, um das Verschweißen der Berührungsoberflächen zu erzeugen.
8. Vorrichtung nach Anspruch 7, dadurch gekennzeichnet, daß der Fortsatz (802) und die Wandungen des Hohlraums (822) gleiches thermoplasti- sches Material aufweisen.
9. Vorrichtung nach Anspruch 8, dadurch gekennzeichnet, daß das thermoplastische Material Acylnitril- Butadien-Styrol umfaßt.
10. Vorrichtung nach Anspruch 9, dadurch gekennzeichnet, daß die Geschwindigkeit, mit der sich der Fort-

satz durch den Hohlraum bewegt, 50 Zoll/Sekunde (127 cm/s) übersteigt.

Revendications

1. Un procédé pour souder ensemble des pre- mière (10) et seconde (20) pièces thermoplas- tiques, caractérisé en ce que la première pièce comprend une tige (12), et la seconde pièce comprend une cavité (22) ayant pratiquement la même forme générale que la tige, mais une section droite moyenne légèrement inférieure, et en ce que le procédé comprend les étapes suivantes : on introduit la tige de la première partie dans la cavité de la seconde partie ; et on pousse plus profondément la tige dans la cavité avec une vitesse suffisante pour provo- quer une fusion de la matière thermoplastique des pièces, dans au moins une région dans laquelle la tige et la cavité sont en contact, la fusion de la matière thermoplastique étant oc- casionnée par le contact avec friction dans une direction axiale, pendant la poussée axiale de la tige dans la cavité, grâce à quoi le soudage est réalisé après le refroidissement de la ma- tière thermoplastique fondue.
2. Le procédé de la revendication 1, dans lequel la matière thermoplastique des première (10) et seconde (20) parties est identique.
3. Le procédé de la revendication 2, dans lequel la matière plastique consiste en acrylonitrile- butadiène-styrène.
4. Le procédé de la revendication 3, dans lequel la vitesse d'insertion de la tige (12) dans la cavité (22) dépasse 127 cm/s.
5. Le procédé de la revendication 1, dans lequel la section droite de la tige (12) conserve sa forme générale, mais s'élargit progressivement sur sa longueur à partir de son point d'entrée initial dans la cavité (22).
6. Le procédé de la revendication 5, dans lequel la section droite de la tige (12) est pratique- ment circulaire.
7. Appareil pour joindre de façon permanente des première (810) et seconde (820) parties, la première partie comprenant une tige (802) qui est formée par une matière thermoplastique, et la seconde partie comprenant une cavité (822) qui a pratiquement la même forme que la tige mais qui a une section droite moyenne légè- rement plus petite et qui a des parois consti- tuées par la matière thermoplastique, CARAC-

TERISE PAR : un dispositif de maintien (820) pour supporter l'une au moins des première et seconde parties avant la jonction permanente de celles-ci ; et des moyens (900) pour pousser l'une contre l'autre les première et seconde parties, d'une manière telle que la tige se déplace à travers la cavité à une vitesse suffisante pour provoquer le soudage de leurs surfaces en contact.

5

10

8. L'appareil de la revendication 7, dans lequel la tige (802) et les parois de la cavité (822) consistent en une matière thermoplastique identique.

15

9. L'appareil de la revendication 8, dans lequel la matière thermoplastique consiste en acrylonitrile-butadiène-styrène.

10. L'appareil de la revendication 9, dans lequel la vitesse à laquelle la tige se déplace à travers la cavité dépasse 127 cm/s.

20

25

30

35

40

45

50

55

FIG. 1





FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7

